

# Ultramid® A3EG7 BK00564

Polyamide 66

BASF Corporation

## Message:

Ultramid A3EG7 BK00564 is a 35% glass fiber reinforced, pigmented black, injection molding PA66 grade for machinery components and housings of high stiffness and dimensional stability.

### Applications

Typical applications include lamp socket housings, cooling fans, insulating profile for aluminium window frames, water containers for automotive cooling systems, as well as electrically insulating parts.

General Information			
UL YellowCard	E36632-531621		
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Features	Good Dimensional Stability		
	High Stiffness		
	Oil Resistant		
Uses	Automotive Applications		
	Containers		
	Electronic Insulation		
	Housings		
	Machine/Mechanical Parts		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm <sup>3</sup>	ISO 1183
Water Absorption			ISO 62
Saturation, 23°C	5.0	%	
Equilibrium, 23°C, 50% RH	1.6	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	190	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.8	%	ISO 527-2
Flexural Modulus (23°C)	10000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	9.5	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	250	°C	ISO 75-2/A

Melting Temperature (DSC)	260	°C	ISO 3146
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	0.15	%	
Processing (Melt) Temp	280 to 305	°C	
Mold Temperature	80.0 to 90.0	°C	
Injection Pressure	3.50 to 12.5	MPa	
Injection Rate	Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

