

Karina IVORY PVC COMPOUND -E 858-35/1-DY-IS-AS

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

OIL AND UV RESISTANT PVC COMPOUND.

General Information			
Features	Good UV Resistance		
	Oil Resistant		
Appearance	Ivory		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.39 to 1.45	g/cm ³	ASTM D792
Color	OK		ME 12
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	86 to 90		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 14.7	MPa	UL 1581
Tensile Elongation (Yield)	> 200	%	UL 1581
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ²	> 14.7	MPa	UL 1581
Tensile Elongation ³ (Break)	> 180	%	UL 1581
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity ⁴	> 2.0E+14	ohms·cm	ASTM D257
NOTE			
1.	24 hr		
2.	Aged in Air for 168 hr at 121°C		
3.	Aged in Air for 168 hr at 121°C		
4.	24 hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

