Hifax TYC 1190P 3004 BLACK

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Hifax TYC 1190P 3004 BLACK high melt flow, 1,600 MPa flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has a very good balance of properties and processability. It is typically used for molded-in color automotive bumper fascia applications.

For regulatory compliance information, see Hifax TYC 1190P 3004 BLACK Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

| General Information | | | |
|---------------------------------------|---------------------------------|----------|-------------|
| Features | Good dimensional stability | | |
| | Rigid, good | | |
| | Impact resistance, good | | |
| | Workability, good | | |
| | High liquidity | | |
| | | | |
| Uses | Car anti-collision bar | | |
| | Application in Automobile Field | | |
| | Automotive exterior parts | | |
| | | | |
| Appearance | Black | | |
| Processing Method | Injection molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density (23°C) | 1.01 | g/cm³ | ISO 1183/A |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 25 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield, 23°C) | 17.0 | MPa | ISO 527-2 |
| Tensile Strain (Break, 23°C) | > 500 | % | ISO 527-2 |
| Flexural Modulus (23°C) | 1600 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| | | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

kJ/m²

ISO 179/1eA

Recommended distributors for this material

Charpy Notched Impact Strength (23°C)

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

