

Sylvin 9848-75FR Brown 7319

Flexible Polyvinyl Chloride
Sylvin Technologies Incorporated

Message:
Sylvin 9848-75FR Brown 7319 Is A Flexible Vinyl Compound Developed For Injection Molding Applications That Require Better Flame Resistance Than Our General Purpose Grade.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Flexibility		
Appearance	Brown		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	75		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	11.7	MPa	ASTM D638
Tensile Elongation (Break)	380	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	56.9	kN/m	ASTM D624
Thermal	Nominal Value	Unit	
Melting Temperature	163 to 174	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT