

VYLOPET® EMC605P

Polybutylene Terephthalate + PET

TOYOBO America, Inc.

Message:

VYLOPET® EMC605P is a polybutylene terephthalate PET (PBT PET) product. It is available in North America.

Features include:

flame retardant/rated flame

Flame Retardant

beautiful

General Information			
Features	Good appearance		
	Flame retardancy		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm³	ASTM D792
	1.2		
Molding Shrinkage - Flow (3.00 mm)	1.1	%	ASTM D955
Water Absorption (24 hr)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	48.0	MPa	ASTM D638
Tensile Elongation (Break)	3.2	%	ASTM D638
Flexural Modulus	3500	MPa	ASTM D790
Flexural Strength (Yield)	80.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	185	°C	ASTM D648
1.8 MPa, not annealed	80.0	°C	ASTM D648
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms · cm	ASTM D257
Dielectric Strength (2.00 mm)	24	kV/mm	ASTM D149
Arc Resistance	90.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method

Flame Rating	V-0	UL 94
Additional Information		
Ball Pressure Temperature, UL746, Method B: 205 °CComparative Tracking Index, IEC Pub1.112: Class 3		
Injection	Nominal Value	Unit
Drying Temperature	140	°C
Drying Time	3.0	hr
Processing (Melt) Temp	265	°C
Mold Temperature	80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT