# Geon™ Vinyl Flexible A85UB

## Flexible Polyvinyl Chloride

### PolyOne Corporation

#### Message:

Geon™ Vinyl Flexible A85UB is a Flexible Polyvinyl Chloride product. It can be processed by extrusion or injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Flexible A85UB include hose/tubing and construction applications.

Characteristics include:

Flame Rated

**UV** Stabilized

General Information			
Additive	Biocide		
	UV Stabilizer		
Features	UV Absorbing		
Uses	Flooring		
	Hose		
	Tubing		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	85		
Shore A, 15 sec	79		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>			ASTM D638
Break	16.5	MPa	
100% Strain	8.27	MPa	
Tensile Elongation <sup>2</sup> (Break)	420	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>3</sup>	73.6	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-32.8	°C	ASTM D746
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94

Injection	Nominal Value	Unit	
Processing (Melt) Temp	193 to 204	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	174 to 179	°C	
NOTE			
1.	510 mm/min		
2.	510 mm/min		
3.	Die C, 510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

