

Rilsamid® AZM 30 Noir T6LD

Polyamide 12

Arkema

Message:

Rilsamid ® AZM 30 Noir T6LD is a fibreglass reinforced polyamide 12. This black coloured grade is designed for injection.

MAIN APPLICATIONS

Quick connectors.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Uses	Connectors		
Appearance	Black		
Processing Method	Injection Molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
	Secant Modulus vs. Strain (ISO 11403-1)		
	Shear Modulus vs. Temperature (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/5.0 kg)	11.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	80		
Shore D, 15 sec	78		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7300	MPa	ISO 527-2
Tensile Stress (Break)	105	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Flexural Modulus	5900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	10	kJ/m ²	
23°C	14	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	80	kJ/m ²	
23°C	71	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	180	°C	ISO 11357-3
Flammability	Nominal Value		Test Method

Flame Rating (0.800 mm)	HB	UL 94
Additional Information	Nominal Value	Test Method
ISO Shortname	PA12, MHLR, 18-070, GF 30	ISO 1874
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	4.0 to 8.0	hr
Processing (Melt) Temp	250 to 280	°C
Mold Temperature	40.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

