

REXtac® APAO RT 2215

Polyalphaolefin
Huntsman Corporation

Message:

REXtac® APAO RT 2215 is a polyα-olefin (PAO) product. It is available in North America. REXtac® APAO RT 2215 applications include glue/gummed paper, sealing applications and food contact applications. The main characteristics are: copolymer.

General Information			
Features	Copolymer		
Uses	Sealant		
	Adhesive		
Agency Ratings	FDA 21 CFR 175.105		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.858	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	0.869	MPa	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-22.2	°C	DSC
Fill Analysis	Nominal Value	Unit	
Melt Density (191°C)	0.740	g/cm ³	
Additional Information			

Melt Viscosity, ASTM D3236, 300°F: 6600 cpsMelt Viscosity, ASTM D3236, 325°F: 3100 cpsMelt Viscosity, ASTM D3236, 350°F: 2200 cpsMelt Viscosity, ASTM D3236, 375°F: 1500 cpsMelt Viscosity, ASTM D3236, 400°F: 1200 cpsNeedle Penetration, ASTM D1321, 25°C: 2.0 mmSoftening Point by Ring and Ball, ASTM E28: 290°FShear Adhesion Failure Temp. (SAFT), Kraft/Kraft, Huntsman Method: 234°FOpen Time, Kraft/Kraft, 25°C, Huntsman Method: 10 secondsFlashpoint, COC, ASTM D93: >450°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT