# Huafon T25H

### Polyamide 66

Huafon Group Co., Ltd.

#### Message:

T25H is light low viscosity, thermo-stability and special product for industrial yarn.

**Typical Applications** 

T25H is used in tire cord, conveyor belt, wool woven bags products.

General Information				
Features	Good Thermal Stability			
	Low Viscosity			
Uses	Bags			
	Conveyors			
	Industrial Applications			
	Yarn			

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm³	ISO 1183
Apparent Density	0.70	g/cm³	Internal Method
Particle Size	2.20 to 2.80	g/100 pellets	Internal Method
Relative Viscosity	2.48 to 2.56		Internal Method
Water Content	< 5000	mg/kg	Internal Method
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature <sup>1</sup>	261	°C	ASTM D3418
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

