

Elastron® G G601.A60.N

Styrene Ethylene Butylene Styrene Block Copolymer

Elastron USA, Inc.

Message:

A soft, colorable halogen free flame retardant (HFFR) SEBS based thermoplastic elastomer (TPE) compound with superior UV resistance.
Bondable to: PP, EVA, PE

General Information	
UL YellowCard	E336670-100940833
Additive	Flame Retardant
Features	Block Copolymer
	Bondability
	Flame Retardant
	Good Colorability
	Good UV Resistance
	Halogen Free
Soft	
RoHS Compliance	RoHS Compliant
Appearance	Natural Color
Forms	Pellets
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	2.0	%	
Across Flow	0.92	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	1.90	MPa	
300% Strain	2.50	MPa	
Tensile Strength (Break)	3.50	MPa	ASTM D412
Tensile Elongation (Break)	500	%	ASTM D412
Tear Strength	22.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 22 hr	12	%	

70°C, 22 hr	48	%
100°C, 22 hr	75	%
Flammability	Nominal Value	Test Method
Flame Rating	V-0	UL 94
Additional Information	Nominal Value	Test Method
Ozone Resistance - Stressed	No Cracks	ASTM D518
Injection	Nominal Value	Unit
Drying Temperature	90.0	°C
Drying Time	2.0	hr
Suggested Max Regrind	20	%
Rear Temperature	145 to 175	°C
Middle Temperature	155 to 185	°C
Front Temperature	160 to 190	°C
Nozzle Temperature	175 to 205	°C
Mold Temperature	25.0 to 50.0	°C
Extrusion	Nominal Value	Unit
Drying Temperature	90.0	°C
Drying Time	2.0	hr
Cylinder Zone 1 Temp.	150 to 170	°C
Cylinder Zone 2 Temp.	155 to 175	°C
Cylinder Zone 3 Temp.	165 to 185	°C
Cylinder Zone 4 Temp.	175 to 205	°C
Cylinder Zone 5 Temp.	180 to 210	°C
Die Temperature	190 to 210	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

