KRATON® D1116 E

Styrene Butadiene Styrene Block Copolymer

Kraton Polymers LLC

Message:

Kraton D1116 E is a clear, radial triblock copolymer based on styrene and butadiene with a polystyrene content of 23%. It is supplied from Europe in the physical form identified below.

Kraton D1116 ES - supplied as porous pellets dusted with an amorphous silica

Kraton D1116 ESM - supplied as powder dusted with an amorphous silica

Kraton D1116 E is used as a modifier of bitumen and polymers. It is also suitable as an ingredient in formulating compounds for footwear applications and may be used in formulating adhesives, sealants, and coatings.

| General Information | | | |
|---------------------------------|-----------------------|-------|-----------------|
| Additive | Antioxidant | | |
| Features | Antioxidant | | |
| | Block Copolymer | | |
| | | | |
| Uses | Adhesives | | |
| | Asphalt Modification | | |
| | Coating Applications | | |
| | Compounding | | |
| | Footwear | | |
| | Plastics Modification | | |
| | Sealants | | |
| | | | |
| Appearance | Clear/Transparent | | |
| Forms | Pellets | | |
| | Powder | | |
| | | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.940 | g/cm³ | ISO 2781 |
| Solution Viscosity ¹ | 2000 to 3000 | mPa·s | Internal Method |
| Bound Styrene | 21.5 to 24.1 | % | Internal Method |
| Antioxidant Additive | > 0.14 | % | |
| Ash Content - ES | < 0.35 | % | ISO 247 |
| Total Extractables | < 1.0 | % | Internal Method |
| Volatile Matter | < 0.30 | % | Internal Method |
| NOTE | | | |
| 1. | 20.0%w Toluene, 25°C | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

