

DynaPath™ 167NL

Polypropylene

Polymer Dynamix

Message:

Conductive PP

Features:

Conductive

Good Dimensional Stability

Excellent Processability

Applications:

Aerospace

Electronics

Industrial

General Information			
Features	Good dimensional stability		
	Conductivity		
	Workability, good		
Uses	Electrical/Electronic Applications		
	Industrial application		
	Aerospace applications		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0 - 10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	20.7	MPa	ASTM D638
Tensile Elongation (Break)	> 10	%	ASTM D638
Flexural Modulus	758	MPa	ASTM D790
Flexural Strength	22.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	750	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+6	ohms	ASTM D257
Volume Resistivity	< 1.0E+6	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	48.9 - 60.0	°C	
Drying Time	2.0	hr	

Rear Temperature	191 - 199	°C
Middle Temperature	196 - 204	°C
Front Temperature	199 - 210	°C
Nozzle Temperature	202 - 213	°C
Processing (Melt) Temp	210 - 216	°C
Mold Temperature	26.7 - 60.0	°C
Injection Pressure	34.5 - 55.2	MPa
Injection Rate	Moderate	
Back Pressure	0.345 - 0.689	MPa
Screw Speed	40 - 70	rpm
Clamp Tonnage	2.8 - 5.5	kN/cm ²
Extrusion	Nominal Value	Unit
Drying Temperature	48.9 - 60.0	°C
Drying Time	2.0	hr
Cylinder Zone 1 Temp.	188 - 196	°C
Cylinder Zone 3 Temp.	193 - 202	°C
Cylinder Zone 5 Temp.	199 - 210	°C
Melt Temperature	204 - 216	°C
Die Temperature	199 - 216	°C
Extrusion instructions		

Screw Speed: 25 to 100 RPM

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT