

POLIMAXX MH-1

Acrylonitrile Butadiene Styrene

IRPC Public Company Limited

Message:

MH-1 is a general purpose grade of ABS resin for injection molding process with medium impact resistance. It is designed for household products. It also meets the requirement of food contact regulation and USP class VI.

General Information			
UL YellowCard	E132283-222076		
Features	Food Contact Acceptable		
	General Purpose		
	Medium Impact Resistance		
Uses	General Purpose		
	Household Goods		
Agency Ratings	USP Class VI		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	18	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C, 6.35 mm)	116		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	52.0	MPa	ASTM D638
Flexural Modulus (23°C)	2260	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	68.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.35 mm)	250	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 6.35 mm	94.0	°C	
1.8 MPa, Unannealed, 6.35 mm	86.0	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 5.0	hr	
Processing (Melt) Temp	190 to 240	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

