

Rhelon G1030H-00

Polyamide 6
RheTech, Inc.

Message:

Rhelon G1030H-00 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber. It can be processed by injection molding and is available in North America. Primary characteristic: heat stabilizer.

| General Information | | | |
|---|----------------------------------|-------------------|-------------|
| Filler / Reinforcement | Glass Fiber,30% Filler by Weight | | |
| Additive | Heat Stabilizer | | |
| Features | Heat Stabilized | | |
| Appearance | Natural Color | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.39 | g/cm ³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.20 to 0.40 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 168 | MPa | ASTM D638 |
| Tensile Elongation | | | ASTM D638 |
| Yield | 3.0 | % | |
| Break | 3.0 | % | |
| Flexural Modulus | 8960 | MPa | ASTM D790 |
| Flexural Strength | 241 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 130 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed) | 212 | °C | ASTM D648 |
| Peak Melting Temperature | 216 | °C | ASTM D789 |
| CLTE - Flow | 5.3E-6 | cm/cm/°C | ASTM D696 |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 79.4 | °C | |
| Suggested Max Moisture | 0.20 | % | |
| Suggested Max Regrind | 25 | % | |
| Rear Temperature | 218 to 235 | °C | |
| Middle Temperature | 241 to 263 | °C | |
| Front Temperature | 246 to 268 | °C | |
| Nozzle Temperature | 246 to 268 | °C | |
| Processing (Melt) Temp | 249 to 266 | °C | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

