

# Kinta NB5010G

Polycarbonate

Kinta Technology (Hong Kong) Co., Ltd.

Message:

Kinta NB5010G is a polycarbonate (PC) product that contains a 10% glass fiber reinforced material. It is available in the Asia-Pacific region. The main characteristics are: flame retardant/rated flame.

| General Information                                              |                                                       |                   |             |
|------------------------------------------------------------------|-------------------------------------------------------|-------------------|-------------|
| Filler / Reinforcement                                           | Glass fiber reinforced material, 10% filler by weight |                   |             |
| Physical                                                         | Nominal Value                                         | Unit              | Test Method |
| Specific Gravity                                                 | 1.23                                                  | g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)                         | 12                                                    | g/10 min          | ASTM D1238  |
| Molding Shrinkage - Flow (3.00 mm)                               | 0.50 - 0.70                                           | %                 | ASTM D955   |
| Water Absorption (23°C, 24 hr)                                   | 0.12                                                  | %                 | ASTM D570   |
| Hardness                                                         | Nominal Value                                         | Unit              | Test Method |
| Rockwell Hardness (R-Scale)                                      | 120                                                   |                   | ASTM D785   |
| Mechanical                                                       | Nominal Value                                         | Unit              | Test Method |
| Tensile Strength <sup>1</sup>                                    | 70.0                                                  | MPa               | ASTM D638   |
| Tensile Elongation <sup>2</sup> (Break)                          | 15                                                    | %                 | ASTM D638   |
| Flexural Modulus <sup>3</sup>                                    | 3450                                                  | MPa               | ASTM D790   |
| Flexural Strength <sup>4</sup>                                   | 105                                                   | MPa               | ASTM D790   |
| Impact                                                           | Nominal Value                                         | Unit              | Test Method |
| Notched Izod Impact (23°C, 3.20 mm)                              | 13.0                                                  | kJ/m <sup>2</sup> | ASTM D256   |
| Thermal                                                          | Nominal Value                                         | Unit              | Test Method |
| Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm) | 128                                                   | °C                | ASTM D648   |
| CLTE - Flow                                                      | 3.2E-5                                                | cm/cm/°C          | ASTM D696   |
| Electrical                                                       | Nominal Value                                         | Unit              | Test Method |
| Volume Resistivity                                               | 1.0E+19                                               | ohms · cm         | ASTM D257   |
| Flammability                                                     | Nominal Value                                         | Unit              | Test Method |
| Flame Rating (3.2 mm)                                            | HB                                                    |                   | UL 94       |
| Injection                                                        | Nominal Value                                         | Unit              |             |
| Drying Temperature                                               | 110 - 120                                             | °C                |             |
| Drying Time                                                      | 4.0                                                   | hr                |             |
| Rear Temperature                                                 | 250 - 270                                             | °C                |             |
| Middle Temperature                                               | 260 - 280                                             | °C                |             |
| Front Temperature                                                | 270 - 290                                             | °C                |             |
| Nozzle Temperature                                               | 270 - 290                                             | °C                |             |
| Processing (Melt) Temp                                           | 260 - 290                                             | °C                |             |
| Mold Temperature                                                 | 80 - 110                                              | °C                |             |
| NOTE                                                             |                                                       |                   |             |

|    |            |
|----|------------|
| 1. | 20 mm/min  |
| 2. | 20 mm/min  |
| 3. | 2.0 mm/min |
| 4. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

