

Exceed™ 1015HA mVLDPE

Metallocene Polyethylene Resin
ExxonMobil Chemical

Message:

Edgede1015HA mVLDPE metallocene very low density polyethylene is a metallocene ethylene-hexene copolymer. The film made of Edgede1015HA mVLDPE very low density polyethylene resin has excellent low temperature toughness, impact strength and puncture resistance. These excellent strength properties and good heat sealing and hot viscosity make it a universal packaging film resin.

General Information			
Additive		Processing aid heat stabilizer	
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	145	MPa	ASTM D882
1% secant, TD	163	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	8.22	MPa	ASTM D882
TD: Yield	7.94	MPa	ASTM D882
MD: Fracture	64.2	MPa	ASTM D882
TD: Fracture	56.5	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	470	%	ASTM D882
TD: Fracture	620	%	ASTM D882
Dart Drop Impact	740	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD	210	g	ASTM D1922
TD	360	g	ASTM D1922
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	33		ASTM D2457
Haze	22	%	ASTM D1003

Legal statement

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

