

Matrixx 34S5070

Polybutylene Terephthalate

The Matrixx Group, Inc.

Message:

Matrixx 34S5070 is a Polybutylene Terephthalate (PBT) material filled with 7.0% glass fiber. It is available in North America.

Important attributes of Matrixx 34S5070 are:

Flame Rated

Flame Retardant

General Information			
Filler / Reinforcement	Glass Fiber,7.0% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.44	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C, 3.18 mm)	75.8	MPa	ASTM D638
Flexural Modulus - Tangent (23°C, 3.18 mm)	3450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm	207	°C	
1.8 MPa, Unannealed, 3.18 mm	175	°C	
RTI Elec	75.0	°C	UL 746
RTI Imp	75.0	°C	UL 746
RTI Str	75.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information	Nominal Value	Unit	Test Method
Reinforcement Content	7.0	%	ASTM D5630

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

