INLUBE PA66SI2IM

Polyamide 66

Infinity LTL Engineered Compounds

Message:

Inlube PTFE, silicone, MoS2 and graphite internally lubricated compounds Offered in all Infinity base resins and can be combined with reinforcements and process additives Provide reduced coefficient of friction and low wear, including enhanced mechanical and thermal propertie

General Information				
Additive	Impact Modifier			
	Silicone Lubricant (2%)			
Features	Good Wear Resistance			
	Impact Modified			
	Low Friction			
	Lubricated			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.10	g/cm ³	ASTM D792	
Specific Volume	0.910	cm³/g		
Molding Shrinkage - Flow	1.5 to 1.8	%	ASTM D955	
Water Absorption (24 hr)	1.4	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Yield)	44.8	MPa	ASTM D638	
Tensile Elongation (Yield)	20 to 30	%	ASTM D638	
Flexural Modulus	1860	MPa	ASTM D790	
Flexural Strength	72.4	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (3.18 mm)	130	J/m	ASTM D256	
Unnotched Izod Impact (3.18 mm)	1400	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (1.8 MPa, Unannealed)	54.4	°C	ASTM D648	
CLTE - Flow	8.1E-5	cm/cm/°C	ASTM D696	
Electrical	Nominal Value	Unit	Test Method	
Surface Resistivity	1.0E+16	ohms	ASTM D257	
Flammability	Nominal Value	Unit	Test Method	
Flame Rating (1.59 mm)	НВ		UL 94	
Injection	Nominal Value	Unit		
Drying Temperature	79.4	°C		

Drying Time	4.0	hr
Processing (Melt) Temp	260 to 302	°C
Mold Temperature	93.3	°C
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm
Vent Depth	0.013 to 0.025	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

