Salflex 262EI

Thermoplastic Polyolefin Elastomer Salflex Polymers Ltd.

Message:

Salflex 262EI is a Thermoplastic Polyolefin Elastomer (TPO (POE)) product. It can be processed by injection molding and is available in North America. Typical application: Automotive. Primary characteristic: impact resistant.

| General Information | | | |
|---------------------------------------|---------------------------|----------|-------------|
| Features | High Impact Resistance | | |
| | Paintable | | |
| | | | |
| Uses | Automotive Applications | | |
| | Automotive Exterior Parts | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.920 | g/cm³ | ISO 1183/A |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 18 | g/10 min | ISO 1133 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore D, 15 sec) | 53 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Flexural Modulus | 730 | MPa | ISO 178 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield) | 12.0 | МРа | ISO 37 |
| Tensile Elongation (Break) | 55 | % | ISO 37 |
| Tear Strength ¹ | 80 | kN/m | ISO 34-1 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact Strength | 48 | kJ/m² | ISO 180/1A |
| Injection | Nominal Value | Unit | |
| Drying Temperature | 60.0 to 75.0 | °C | |
| Drying Time | 2.0 to 4.0 | hr | |
| Rear Temperature | 190 to 220 | °C | |
| Middle Temperature | 200 to 230 | °C | |
| Front Temperature | 210 to 240 | °C | |
| Nozzle Temperature | 210 to 240 | °C | |
| Processing (Melt) Temp | 200 to 220 | °C | |
| Mold Temperature | 27.0 to 60.0 | °C | |
| NOTE | | | |
| 1. | Method Bb, Angle (Nicked) | | |

Page 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

