

INELEC PBTCF30

Polybutylene Terephthalate

Infinity LTL Engineered Compounds

Message:

Inelec carbon fiber, carbon powder, stainless steel fiber, nickel coated carbon fiber and antistatic alloy electrically active compounds

Offered in all Infinity base resins

Provide electrostatic discharge and electrical conductivity. EMI and RFI shielding compounds available

General Information			
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight		
Features	Electrically Conductive		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Specific Volume	0.710	cm ³ /g	
Molding Shrinkage - Flow	0.10 to 0.20	%	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	145	MPa	ASTM D638
Tensile Elongation (Yield)	1.0 to 3.0	%	ASTM D638
Flexural Modulus	15900	MPa	ASTM D790
Flexural Strength	203	MPa	ASTM D790
Shear Strength	55.2	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	59	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	218	°C	ASTM D648
CLTE - Flow	7.2E-6	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	221 to 260	°C	
Mold Temperature	107	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	

Vent Depth	0.013 to 0.025	mm
------------	----------------	----

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT