Maxxam™ MD 4245-59770

Polypropylene Copolymer PolyOne Corporation

Message:

PolyOne's Maxxam™ family of polypropylene- and polyethylene-based products covers a wide range of applications, markets and performance requirements. Standard grades are compounded with calcium carbonate, glass and talc to provide a desired balance of properties including stiffness, durability, impact resistance and heat resistance. Custom grades are available with features such as UV stabilizers, heat stabilizers, custom color, high impact, etc.

General Information				
UL YellowCard	E76261-101413511			
Filler / Reinforcement	Calcium Carbonate,30% Filler by Weight			
Features	Copolymer			
	General Purpose			
	Impact Modified			
Uses	Automotive Applications			
	Construction Applications			
	Consumer Applications			
	General Purpose			
	Industrial Applications			
Appearance	Blue			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.12	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16	1.12	g/cm	ASTIVI DI 32	
kg)	15	g/10 min	ASTM D1238	
Molding Shrinkage - Flow	1.0 to 1.5	%	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength ² (Yield)	20.7	MPa	ASTM D638	
Tensile Elongation ³ (Break)	40	%	ASTM D638	
Flexural Modulus	1930	MPa	ASTM D790	
Flexural Strength	38.6	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	37	J/m	ASTM D256A	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	106	°C	ASTM D648	
Injection	Nominal Value	Unit		

Mold Temperature	16.0 to 50.0	°C	
NOTE			
1.	Procedure A		
2.	Type I, 51 mm/min		
3.	Type I, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

