

Tenac™-C GN755

Acetal (POM) Copolymer
Asahi Kasei Chemicals Corporation

Message:

Tenac™-C GN755 is an Acetal (POM) Copolymer product filled with glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or North America. Applications of Tenac™-C GN755 include engineering/industrial parts and housings.

Characteristics include:

- Flame Rated
- Copolymer
- High Stiffness
- High Strength
- Low Viscosity

General Information	
UL YellowCard	E48285-240816
Filler / Reinforcement	Glass Fiber
Features	Copolymer
	High Stiffness
	High Strength
	Low Viscosity
Uses	Engineering Parts
	Gears
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.59	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage			Internal Method
Flow	0.40 to 0.60	%	
Across Flow	1.0 to 1.2	%	
Water Absorption (23°C, 24 hr, 50% RH)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	79		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ISO 527-2
Tensile Stress			
Break	120	MPa	ISO 527-2
--	120	MPa	ASTM D638
Tensile Elongation			
Break	8.0	%	ASTM D638
Break	2.0	%	ISO 527-2

Flexural Modulus			
--	7940	MPa	ASTM D790
--	7500	MPa	ISO 178
Flexural Strength	188	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m ²	ISO 179
Notched Izod Impact	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	162	°C	ASTM D648
0.45 MPa, Unannealed	165	°C	ISO 75-2/B
1.8 MPa, Unannealed	140	°C	ASTM D648
1.8 MPa, Unannealed	163	°C	ISO 75-2/A
CLTE			
Flow	4.0E-5	cm/cm/°C	ASTM D696
Flow	4.0E-5 to 9.0E-5	cm/cm/°C	ISO 11359-2
Transverse	9.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.750 mm	HB		
1.50 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

