

POBUX 3001G0

Polybutylene Terephthalate
POLYROCKS CHEMICAL CO., LTD

Message:

POBUX 3001G0 is a Polybutylene Terephthalate (PBT) product. It is available in Asia Pacific. Typical application: Electrical/Electronic Applications.
Characteristics include:
Flame Rated
Flame Retardant
Good Dimensional Stability
Rigid

General Information			
Features	Flame Retardant		
	Good Dimensional Stability		
	High Rigidity		
Uses	Electrical Parts		
	Electrical/Electronic Applications		
UL File Number	E253482		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.45	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	70.0	MPa	ASTM D638
Tensile Elongation (Break)	59	%	ASTM D638
Flexural Modulus	88.0	MPa	ASTM D790
Flexural Strength	18.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2600	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	70.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	550	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	UL 94		
1.50 mm	V-0		
3.00 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	

Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	70.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

