

DILAMID® 6 GREY 1225

Polyamide 6

Dilaplast S.p.A.

Message:

DILAMID® 6 GREY 1225 is a polyamide 6 (nylon 6) material. This product is available in Europe, and the processing method is injection molding.
DILAMID® The main characteristics of 6 GREY 1225 are: impact modification.

General Information			
Additive	Impact modifier		
Features	Impact modification		
Appearance	Grey		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Molding Shrinkage - Flow	1.3 - 1.7	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Flexural Modulus	2.00	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	8.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	170	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	18	kV/mm	ASTM D149
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
Additional Information			
Tensile Stress at Yield, ISO 527-1, -2: >50 MPaTensile Strain at Break, ISO 527-1, -2: >20%Comparative Track Index, IEC 60112: >500 V			
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 8.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	220 - 250	°C	
Middle Temperature	230 - 270	°C	
Front Temperature	235 - 275	°C	
Nozzle Temperature	230 - 270	°C	

Processing (Melt) Temp	235 - 275	°C
Mold Temperature	60.0 - 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

