

ELASTOSIL® N 198

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, RTV-1

Wet-Type Gaskets, Automotive & Transportation

Elect. Control Devices/Protect Sensors, Automotive & Transportation

Elect. Control Devices/Protect Sensors, Electronics

Electronic Control Devices, Electrical Industry

Electronic Control Devices, Automotive & Transportation

Electronic Control Devices, Electronics

Bonding & Sealing, Lighting

Bonding & Sealing, Mechanical and Plant Engineering

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Renewable Energies

| General Information | | | |
|---------------------------------------|---------------|-------------------|-------------|
| Uses | Adhesives | | |
| | Bonding | | |
| | Sealants | | |
| Uncured Properties | Nominal Value | Unit | Test Method |
| Color | Grey | | |
| Density | 1.20 | g/cm ³ | ISO 2781 |
| Curing Time | 24 | hr | |
| Skin Forming Time ¹ (23°C) | 30.0 | min | |
| Cured Properties | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 40 | | ISO 868 |
| Tensile Strength | 3.00 | MPa | ISO 37 |
| Tensile Elongation at Break | 300 | % | ISO 37 |
| NOTE | | | |
| 1. | 50% R.H | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT