Epoxies, Ect. 10-2055 HV

Polyurethane

Epoxies, Etc.

Message:

The 10-2055 and 10-2055 HV were developed to produce general purpose, semi flexible polyurethane adhesives for bonding a wide variety of plastic and metal substrates. The flexibility of these adhesives allows bonding to substrates with high coefficients of thermal expansion (CTE) and substrates with different CTE's

The same Iso component is used separately with each Polyol at a convenient 1:1 ratio by volume. The selection of Polyol determines the initial viscosity of the adhesive. 10-2055 produces a light paste consistency similar to honey and 10-2055 HV produces a heavy paste consistency similar to grease. Please note each Iso and Polyol offer good low viscosity handling characteristics and turn thixotropic upon mixing.

General Information			
Appearance	Clear Amber		
Thermal	Nominal Value	Unit	
Thermal Conductivity	0.12	W/m/K	
Electrical	Nominal Value	Unit	
Insulation Resistance ¹	2.4E-11	ohms	
Handle Time (25°C)	25.0	min	
Uncured Properties	Nominal Value	Unit	
Color			
2	Amber		
3	Clear/Transparent		
Mix Ratio by Weight (PBW)			
Part A	100		
Part B	90		
Density			
25°C ⁴	1.05	g/cm³	
25°C ⁵	1.15	g/cm³	
Viscosity			
25°C ⁶	3.0	Pa·s	
25°C ⁷	8.0	Pa·s	
Curing Time	24	hr	
Pot Life (25°C)	3.0 to 4.8	min	
Shelf Life	3	month	
Cured Properties	Nominal Value	Unit	
Shore Hardness (Shore D)	55 to 60		
Electric Strength (3.18 mm)	> 16	kV/mm	
NOTE			
1.	25°C		
2.	Part A		
3.	Part B		
4.	Part B		

5.	Part A	
6.	Part B	
7	Part A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

