

# InnoTuf® TP-4007

Polyurethane Thermoset Elastomer

Innovative Polymers, Inc.

Message:

TP-4007 is an impact resistant polyurea formulated for vacuum assisted casting systems and short mold cycle times. Excellent physical properties can be obtained without the utilization of mercury, MOCA, or TDI.

General Information			
Features	Fast Molding Cycle		
	High Heat Resistance		
	High Impact Resistance		
RoHS Compliance	RoHS Compliant		
Appearance	Amber		
Processing Method	Vacuum Casting		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Cured	1.20	g/cm <sup>3</sup>	
Hardener	1.20	g/cm <sup>3</sup>	
Base Resin	1.20	g/cm <sup>3</sup>	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D2566
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1970	MPa	ASTM D790
Flexural Strength	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	171	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 50		
Hardener	Mix Ratio by Weight: 50		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		
Demold Time (66°C)	60	min	

Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
38°C <sup>1</sup>	0.40	Pa·s	
38°C <sup>2</sup>	0.60	Pa·s	
38°C <sup>3</sup>	1.0	Pa·s	
Curing Time <sup>4</sup>	25	hr	
Gel Time	8.0 to 12	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75 to 85		ASTM D2240
Tensile Strength	62.1	MPa	ASTM D638
Tensile Elongation at Break	19	%	ASTM D638
NOTE			
1.	Mixed		
2.	Hardener		
3.	Resin		
4.	1 hour at 150°F + 24 hours at 77°F		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

