

Rotec® ABS 5001

Acrylonitrile Butadiene Styrene

ROMIRA GmbH

Message:

Rotec® ABS 5001 is an acrylonitrile butadiene styrene (ABS) material. This product is available in Europe and is processed by extrusion or injection molding.

Rotec® The main features of ABS 5001 are:

flame retardant/rated flame

Impact resistance

General Information	
UL YellowCard	E148878-223642
Features	Impact resistance, high
UL File Number	E148878
Forms	Particle
Processing Method	Extrusion Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	18	g/10 min	ISO 1133
Molding Shrinkage	0.50 - 0.70	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2100	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	20	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	2200	MPa	ISO 178
Flexural Stress ² (23°C)	70.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	21	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	97.0	°C	ISO 306/B50
CLTE - Flow (23 to 55°C)	9.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.17	W/m/K	ISO 8302

Flammability	Nominal Value	Test Method
Flame Rating (1.50 mm)	HB	UL 94

Additional Information

The value listed as Thermal Conductivity ISO 8302, was tested in accordance with DIN 52612.

Injection	Nominal Value	Unit
-----------	---------------	------

Drying Temperature	< 80.0	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.050	%
Suggested Max Regrind	5	%
Rear Temperature	210 - 250	°C
Middle Temperature	210 - 250	°C
Front Temperature	210 - 250	°C
Processing (Melt) Temp	< 260	°C
Mold Temperature	40.0 - 80.0	°C
Injection Rate	Fast	

Injection instructions

Screw rotation speed: moderate to high Back pressure: low to moderate Injection pressure: tool depending

Extrusion	Nominal Value	Unit
Drying Temperature	< 80.0	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	< 0.050	%
Cylinder Zone 1 Temp.	190 - 210	°C
Cylinder Zone 2 Temp.	190 - 210	°C
Cylinder Zone 3 Temp.	190 - 210	°C
Cylinder Zone 4 Temp.	190 - 210	°C
Cylinder Zone 5 Temp.	190 - 210	°C
Melt Temperature	< 245	°C

NOTE

1. 2.0 mm/min
2. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT