

Raditer® B RVA100

Polybutylene Terephthalate

Radici Plastics

Message:

PBT/ASA blend 10% Glass fibre reinforced injection moulding grade. For items with enhanced stiffness. High dimensional stability and Low warpage. Good surface quality. Natural colour.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Good dimensional stability		
	Low warpage		
	Rigid, good		
	Excellent appearance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4200	MPa	ISO 527-2
Tensile Stress (Break)	75.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/eA
-30°C	4.5	kJ/m ²	ISO 179/eA
23°C	5.5	kJ/m ²	ISO 179/eA
Charpy Unnotched Impact Strength			ISO 179/eU
-30°C	30	kJ/m ²	ISO 179/eU
23°C	45	kJ/m ²	ISO 179/eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	110	°C	ISO 75-2/Af
Melting Temperature (DSC)	225	°C	ISO 3146
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			

The value listed as Melting Temperature, ISO 3146, was tested in accordance with ISO 11357-1-3 at a heating rate of 10°C/min.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT