TechnoElast 9085

Styrene Ethylene Butylene Styrene Block Copolymer

TechnoCompound GmbH

Message:

The TechnoElast TPE compounds are a new, innovative product range of TechnoCompound based on styrene block copolymers. TechnoElast TPE compounds with adjustable melt flow rates possess good insulation properties, good workability, offer good thermal stability, outstanding absorption characteristics as well as elastic memory.

General Information									
Features	Block Copolymer								
	Resilient recovery, excellent Good liquidity Thermal stability, good								
					Uses	Membrane key switch			
						Electrical/Electronic Applications			
Electrical housing									
Insulating material									
Seals									
Parts under the hood of a car									
Application in Automobile Field									
Car interior parts									
Automotive exterior parts									
Shell									
Forms	Particle								
Processing Method	Injection molding								
Physical	Nominal Value	Unit	Test Method						
Density	1.13	g/cm³	ISO 1183						
Hardness	Nominal Value	Unit	Test Method						
Durometer Hardness (Shore A)	85		ISO 868						
Mechanical	Nominal Value	Unit	Test Method						
Tensile Stress (Break)	12.0	MPa	ISO 527-2						
Tensile Strain (Break)	250	%	ISO 527-2						
Additional Information									

tested in accordance with DIN 53504. The value listed as Tensile Strain at Break, ISO 527-1, -2, was tested in accordance with DIN 53504. Moisture Content, Infared 105°C, 15 min: 250%

Injection	Nominal Value	Unit
Drying Temperature	60.0 - 80.0	°C
Drying Time	2.0	hr

Processing (Melt) Temp	180 - 220	°C
Mold Temperature	20.0 - 40.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

