

Eltex® PF6212LJ

Metallocene Linear Low Density Polyethylene

INEOS Olefins & Polymers Europe

Message:

Eltex® PF6212LJ is a metallocene LLDPE grade produced in Europe

Benefits & Features

Eltex® PF6212LJ is a polyethylene copolymer containing hexene-1 as the comonomer produced with a metallocene catalyst. It offers the following properties:

- Extremely high impact strength
- Excellent optical properties
- Very good bubble stability and extrudability
- Low temperature sealing characteristics

Applications

Eltex® PF6212LJ has been developed for use in food packaging and other thin film applications where excellent mechanical and optical performance is required. In addition, Eltex® PF6212LJ is a version intended for lamination applications.

If corona treatment is necessary, the level should normally be in the range 38-48 mN/m.

General Information			
Additive	Antiblock (300 ppm) 2		
	Antioxidant		
	Erucamide Slip (1000 ppm)		
Features	Antiblocking		
	Antioxidant		
	Copolymer		
	Food Contact Acceptable		
	Good Processability		
	Hexene Comonomer		
	High Impact Resistance		
	Low Density		
	Low Temperature Heat Sealability		
	Opticals		
Uses	Slip		
	Film		
	Food Packaging		
RoHS Compliance	Laminates		
	Contact Manufacturer		
Forms	Pellets		
Processing Method	Film Extrusion		
	Laminating		
Physical	Nominal Value	Unit	Test Method

Density (23°C)	0.920	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.3	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction	< 0.25		ASTM D1894
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	μm	
Tensile Modulus			ISO 527-3
1% Secant, MD : 25 μm	180	MPa	
1% Secant, TD : 25 μm	200	MPa	
Tensile Stress			ISO 527-3
MD : Yield, 25 μm	9.00	MPa	
TD : Yield, 25 μm	10.0	MPa	
MD : Break, 25 μm	65.0	MPa	
TD : Break, 25 μm	60.0	MPa	
Tensile Elongation			ISO 527-3
MD : Break, 25 μm	550	%	
TD : Break, 25 μm	670	%	
Dart Drop Impact (25 μm)	> 1000	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD : 25 μm	200	g	
TD : 25 μm	440	g	
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature ¹	105 to 118	°C	ASTM D3418
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 25.0 μm)	62		ASTM D2457
Haze (25.0 μm)	8.0	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	190 to 230	°C	
NOTE			
1.	2nd heating		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT