

Sumitomo PP AZ564G

Polypropylene Copolymer
Sumitomo Chemical Asia

Message:

Applications For industrial applications such as large crates, washing machine parts, electrical appliances, and thin walled articles.
Characteristics High flow, high impact, high stiffness and high heat stability.

General Information			
Features	Block Copolymer		
	High Flow		
	High Heat Resistance		
	High Impact Resistance		
	High Stiffness		
Uses	Appliance Components		
	Appliances		
	Crates		
	Thin-walled Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	39	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Across Flow	1.6	%	
Flow	1.4	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness	86		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	24.0	MPa	
Break	16.0	MPa	
Flexural Modulus	1280	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ASTM D256
-20°C	5.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (0.45 MPa, Unannealed)	118	°C	ASTM D648
Vicat Softening Temperature	149	°C	ASTM D1525 ¹
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	
Mold Temperature	20.0 to 70.0	°C	
NOTE			

1. Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

