

# ECONAMID® 6ST2

Polyamide 6

DOMO Engineering Plastics SPA

Message:

Polyamide 6, good impact resistance, for injection moulding.

General Information			
Features	Good Impact Resistance		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	135	cm <sup>3</sup> /g	ISO 307
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2400	MPa	ISO 527-2/1
Tensile Stress (Yield)	60.0	MPa	ISO 527-2/50
Tensile Strain (Break)	> 50	%	ISO 527-2/50
Flexural Stress <sup>1</sup>	85.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	24	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength (23°C)	20	kJ/m <sup>2</sup>	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	No Break		ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	145	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	175	°C	ISO 306/B50
Melting Temperature	222	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating (0.800 mm)	HB		UL 94
Injection	Nominal Value	Unit	Test Method
Drying Temperature	75.0 to 85.0	°C	

Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	60.0 to 90.0	°C

NOTE

1. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

