Lifoflex® UV FLAM 80600

Thermoplastic Elastomer

Müller Kunststoffe GmbH

Message:

Lifoflex® UV FLAM 80600 is a Thermoplastic Elastomer (TPE) material. It is available in Europe for extrusion or injection molding. Important attributes of Lifoflex® UV FLAM 80600 are:

Flame Rated

RoHS Compliant

Flame Retardant

Good Adhesion

Good Flexibility

Typical applications include:

Engineering/Industrial Parts

Construction Applications

Electrical/Electronic Applications

Wire & Cable

General Information											
Features	Flame Retardant										
	Good Adhesion Good Flexibility Good Processability Halogen Free Low Compression Set Low Smoke Emission										
						Low Toxicity					
						Uses	Building Materials				
							Cable Jacketing				
							Electrical Parts				
	Gaskets										
Grommets											
Profiles											
Agency Ratings	EU 2003/11/EC										
RoHS Compliance	RoHS Compliant										
Processing Method	Extrusion										
	Injection Molding										
Physical	Nominal Value	Unit	Test Method								
Density	1.03	g/cm³	ISO 1183/A								
Hardness	Nominal Value	Unit	Test Method								
Shore Hardness (Shore A, 3 sec)	80		DIN 53505								
Elastomers	Nominal Value	Unit	Test Method								

Tensile Stress - Flow (Yield)	7.50	MPa	DIN 53504
Tensile Elongation - Flow (Break)	770	%	DIN 53504
Compression Set			ISO 815
23°C, 72 hr	37	%	
70°C, 22 hr	63	%	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.00 mm)	V-0		UL 94
	850		

Glow Wire Flammability Index (3.00 mm)

650

°C

IEC 60695-2-12

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

