

TECHNYL® A 218G2 V30 BLACK 34 N

Polyamide 66
Solvay Engineering Plastics

Message:

TECHNYL® A 218G2 V30 Black 34N is a polyamide 66, reinforced with 30% of glass fiber, heat stabilized, for injection molding. The product is available in black color.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Heat Stabilizer		
Features		Glycol Resistant		
		Heat Stabilized		
Uses		Automotive Applications		
Agency Ratings		UU 453/2010/EC		
RoHS Compliance		RoHS Compliant		
Appearance		Black		
Processing Method		Injection Molding		
Part Marking Code (ISO 11469)		>PA66-GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.37	--	g/cm ³	ISO 1183/A
Molding Shrinkage				Internal Method
Across Flow	0.80	--	%	
Flow	0.50	--	%	
Water Absorption (23°C, 24 hr)	0.80	--	%	ISO 62
Molding Shrinkage Isotropy	0.620	--		Internal Method
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	7500	MPa	ISO 527-2/1A
Tensile Stress (Break)	195	140	MPa	ISO 527-2/1A
Tensile Strain (Break)	3.0	4.0	%	ISO 527-2/1A
Flexural Modulus	9200	6400	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	11	15	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				
-- ¹	67	--	kJ/m ²	ISO 179/1fU
23°C	87	110	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength (23°C)	10	18	kJ/m ²	ISO 180/1A

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	250	--	°C	ISO 75-2/Af
Melting Temperature	263	--	°C	ISO 11357-3
CLTE - Flow (23 to 85°C)	2.0E-5	--	cm/cm/°C	ISO 11359-2
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	70.0 to 100		°C	
NOTE				

1. After ageing in water/glycol for 200 hr at 135°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT