

LNP™ COLORCOMP™ FR15C compound

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

COLORCOMP* FR15C is a compound based on ABS (non-PBBE additive) containing Flame Retardant. Added features include: Good Property/Toughness, Excellent Moldability.

General Information			
Additive	Flame retardancy		
Features	Good formability		
	Good toughness		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.20	g/cm ³	ASTM D792
--	1.19	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	4.0	g/10 min	ASTM D1238
220°C/5.0 kg	10	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2340	MPa	ASTM D638
Tensile Strength			
Yield ²	41.4	MPa	ASTM D638
Yield	41.3	MPa	ISO 527-2/50
Fracture ³	35.2	MPa	ASTM D638
Fracture	31.3	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	2.3	%	ASTM D638
Yield	2.1	%	ISO 527-2/50
Fracture ⁵	9.0	%	ASTM D638
Fracture	34	%	ISO 527-2/50
Flexural Modulus ⁶ (50.0 mm Span)	2720	MPa	ASTM D790
Flexural Strength ⁷ (Yield, 50.0 mm Span)	71.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁸ (23°C)	20	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C	210	J/m	ASTM D256

-30°C ⁹	6.5	kJ/m ²	ISO 180/1A
23°C ¹⁰	19	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	33.9	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	82.2	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	70.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹¹	73.4	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	86.1	°C	ASTM D1525 ¹²
--	81.2	°C	ISO 306/B50
--	84.1	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831
Flow: -40 to 40°C	8.5E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	8.6E-5	cm/cm/°C	ASTM E831
RTI Elec	60.0	°C	UL 746
RTI Imp	60.0	°C	UL 746
RTI	60.0	°C	UL 746
Electrical	Nominal Value		Test Method
Arc Resistance ¹³	PLC 7		ASTM D495
Comparative Tracking Index (CTI)	PLC 2		UL 746
High Amp Arc Ignition (HAI)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.5 mm	V-0		UL 94
2.5 mm	5VA		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (200°C, 1000 sec ⁻¹)	290	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	82 - 88	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	6.0	hr	
Suggested Max Moisture	0.10	%	
Suggested Shot Size	50 - 70	%	
Rear Temperature	171 - 182	°C	
Middle Temperature	193 - 204	°C	
Front Temperature	199 - 216	°C	
Nozzle Temperature	199 - 221	°C	
Processing (Melt) Temp	199 - 221	°C	

Mold Temperature	49 - 71	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	30 - 60	rpm
Vent Depth	0.038 - 0.051	mm

NOTE		
1.	5.0 mm/min	
2.	Type 1, 5.0 mm/min	
3.	Type 1, 5.0 mm/min	
4.	Type 1, 5.0 mm/min	
5.	Type 1, 5.0 mm/min	
6.	1.3 mm/min	
7.	1.3 mm/min	
8.	80*10*4 sp=62mm	
9.	80*10*4	
10.	80*10*4	
11.	80*10*4 mm	
12.	标准 B (120°C/h), 载荷2 (50N)	
13.	Tungsten electrode	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

