

Starflam PF0047E

Polyamide 6
Eurostar Engineering Plastics

Message:

Starflam PF0047E is a Halogen Free and Red Phosphorous Free, Flame Retardant, Glass Fiber Reinforced, Polyamide 6 Injection Molding Resin (also known as Starflam EXCP4009)

General Information			
Filler / Reinforcement	Glass Fiber		
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	Low (to None) Phosphorus Content		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	0.20 to 0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ISO 527-2/1
Tensile Stress (Break)	120	MPa	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Flexural Modulus	7000	MPa	ISO 178
Flexural Stress	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ¹ (23°C)	8.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ² (23°C)	45	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed, 64.0 mm Span)	195	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	240 to 250	°C	
Middle Temperature	250 to 260	°C	
Front Temperature	250 to 270	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	50.0 to 90.0	°C	
NOTE			

1.	80*10*4
2.	80*10*4
3.	80*10*4

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

