

# Generic LDPE+EVA

Low Density Polyethylene + EVA

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic LDPE+EVA

This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	0.924 to 0.925	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.99 to 2.5	g/10 min	ASTM D1238
Vinyl Acetate Content	2.5 to 4.1	wt%	
Films	Nominal Value	Unit	Test Method
Tensile Elongation			ASTM D882
MD : Break	340 to 350	%	
TD : Break	510 to 550	%	
Elmendorf Tear Strength - MD	190 to 220	g	ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

