

# Ultrathene® UE650028

Ethylene Vinyl Acetate Copolymer

LyondellBasell Industries

## Message:

Ultrathene UE650028 is an EVA copolymer with excellent flexibility and low temperature properties.

General Information			
Features	Good flexibility		
	Low temperature resistance		
	Compliance of Food Exposure		
Agency Ratings	FDA 21 CFR 175.105		
	FDA 21 CFR 177.1350		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Vinyl Acetate Content	12.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	69.0	°C	ASTM D1525
Melting Temperature	91.0	°C	DSC
Injection	Nominal Value	Unit	
Processing (Melt) Temp	< 221	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

