

ELASTOSIL® LR 3004/30 A/B

Silicone
Wacker Chemie AG

Message:

- Silicone Rubber, LSR
- Molded Parts, Technical, Plastics and Rubber Processing
- Molded Parts, Automotive, Plastics and Rubber Processing
- Molded Parts, Food Contact, Plastics and Rubber Processing
- Molded Seals, Plastics and Rubber Processing
- Vibration Dampers, Automotive & Transportation

General Information	
Features	Fast Cure
	Food Contact Acceptable
	General Purpose
Uses	Automotive Applications
	Automotive Under the Hood
	Gaskets
	Membranes
	Seals
	Valves/Valve Parts
Processing Method	Injection Molding
	Liquid Injection Molding (LIM)

Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.10	g/cm ³	ISO 1183
Viscosity	100	Pa · s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	30		DIN 53505
Tensile Strength	7.40	MPa	DIN 53504
Tensile Elongation at Break	620	%	DIN 53504
Compression Set	9.0	%	DIN ISO 815-B
Tear Strength	26.0	kN/m	ASTM D624B
Rebound Resilience	60	%	DIN 53512
Electric Strength	23	kV/mm	DIN IEC 243
Volume Resistivity	5.0E+15	ohms · cm	DIN IEC 93
Dissipation Factor (50 Hz)	2.0E-4		DIN VDE 0303

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

