LTP LTP8180

Polyphenylene Sulfide Alloy

Chengdu Letian Plastics Co., Ltd

Message:

LTP 8100 serials is reinforced composite materials with high performance based on polyolefin and PPS, and are extensively applied in injection mold to structure and parts of machine, electric appliance and automobiles. It is used to replace materials of PA PBT (PET), PPO (PPE), and PC/ABS serial. The LTP 8100 serials materials have the characteristics of high impact strength, high dimensional stability and low moisture absorption.

General Information				
Filler / Reinforcement	Filler			
Features	Good Dimensional Stability			
	High Impact Resistance			
	Low Moisture Absorption			
Uses	Appliances			
	Automotive Applications			
	Electrical/Electronic Applications			
	Machine/Mechanical Parts			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.30	g/cm³	ASTM D792	
Molding Shrinkage ¹				
Across Flow : 3.00 mm	0.80	%		
Flow : 3.00 mm	0.50	%		
Water Absorption (Saturation)	0.10	%	ASTM D570	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Stress	80.0	МРа	GB/T 1040	
Tensile Strain (Break)	15	%	GB/T 1040	
Flexural Stress	120	MPa	GB/T 1042	
Impact	Nominal Value	Unit	Test Method	
Charpy Notched Impact Strength	18	kJ/m²	GB/T 1043	
Thermal	Nominal Value	Unit	Test Method	
Heat Deflection Temperature	> 165	°C	GB/T 1634	
Electrical	Nominal Value	Unit	Test Method	
Surface Resistivity	2.0E+15	ohms	GB/T 1410	
Volume Resistivity	5.0E+14	ohms·cm	GB/T 1410	
Dielectric Strength	17	kV/mm	ASTM D149	
Dielectric Constant			GB/T 1409	
25°C, 1 kHz	3.20			
25°C, 1 MHz	3.20			

Dissipation Factor			GB/T 1409
25°C, 1 kHz	3.0E-3		
25°C, 1 MHz	3.0E-3		
Flammability	Nominal Value	Unit	Test Method
	НВ		
Flame Rating	V-0		UL 94
NOTE			
1.	80x80x3 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

