

# RTP EMI 260.5 H

Polyamide 66

RTP Company

## Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Stainless steel fiber, 5.0% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Electromagnetic shielding (EMI)		
	Electrostatic discharge protection		
	Antistatic property		
Agency Ratings	MIL B-81705C		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.2 - 1.5	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.5	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2410	MPa	ASTM D638
Tensile Strength	48.3	MPa	ASTM D638
Tensile Elongation (Break)	10	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790
Flexural Strength	65.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	190	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1100	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+2	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94

#### Additional Information

The value listed as Flammability, UL 94, was tested in accordance with RTP test standards. Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 15-18mil/in. Tensile Elongation@Break, ASTM D-638: > 10% Volume Resistivity, ASTM D-257: < 1E2 ohm-cm Surface Resistivity, ASTM D-257: < 1E6 ohm Static Decay, Mil B-81705C: < 2.0 seconds Shielding Effectiveness, ASTM D4935: 30dB

Injection	Nominal Value	Unit
Rear Temperature	274 - 288	°C
Middle Temperature	274 - 288	°C
Front Temperature	274 - 288	°C
Mold Temperature	65.6 - 107	°C
Injection Pressure	68.9 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

