

S&E; Automotive XP44-10MG

Polyvinyl Chloride

S&E; Specialty Polymers, LLC

Message:

PVC weatherable, integral colored, filled, body side end cap molding compound.

General Information			
Filler / Reinforcement	Filler		
Features	Good Weather Resistance		
Uses	Automotive Applications		
Appearance	Colors Available		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	< 1.40	g/cm ³	ISO 1183/A
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	34 to 40		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	> 9.00	MPa	ISO 527-2/1/500
Tensile Strain (Break)	> 75	%	ISO 527-2/1/500
Thermal	Nominal Value	Unit	Test Method
Cold Flexibility	-30	°C	GM 9503P
Accelerated Weathering Duration ¹	< 3.00		SAE J2527
NOTE			

1. after 2000 kj/m²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

