

# Plaskon 3400-2

Epoxy; Epoxide

Cookson Electronics - Semiconductor Products

## Message:

This material is a reduced-stress epoxy molding compound for the encapsulation of a variety of semiconductor devices ranging from small lead count DIPs to medium lead count PLCCs, QFPs and SOICs. It was especially developed for balanced end use properties.

General Information			
Features	Semi-conductive		
	Laser marking		
	Good formability		
	Excellent appearance		
Forms	Liquid		
Processing Method	Resin transfer molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.79	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1.52	MPa	ASTM D790
Flexural Strength	0.0124	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	155	°C	ASTM E1356
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	16	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.0E+15	ohms · cm	ASTM D257
Dielectric Strength	16	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	3.60		ASTM D150
Dissipation Factor (1 kHz)	2.0E-3		ASTM D150
Arc Resistance	180	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.18 mm)	V-0		UL 94
Oxygen Index	32	%	ASTM D2863
Additional Information			
Recommended Storage Temperature: 5°C Life @ 5°C, defined as not more than 40% loss of spiral flow based on original values.: 24 months Life @ 21°C, defined as not more than 40% loss of spiral flow based on original values.: 5 days Life @ 35°C, defined as not more than 40% loss of spiral flow based on original values.: 2 days Spiral Flow, 177°C, 1000 psi: 63 to 87 cm Automatic Orifice Viscosity, 175°C, 1000 psi, 1 mm die length, 1/2 mm diameter: 6 to 13 Pascal sec Ram Follower Gel Time, 177°C: 18 to 22 sec Ash Content: 72 % Hydrolyzable Halides: <10 ppm Cull Hot Hardness, Shore D, 90 sec, 175°C: 75 Arc Resistance, 110v AC 180 sec All test specimens are transfer molded and post cured for 4 hours at 175°C Linear Thermal Expansion, Alpha 1: 20 cm <sup>-6</sup> /cm/°C Linear Thermal Expansion, Alpha 2: 62 cm <sup>-6</sup> /cm/°C			
Injection instructions			

Resin Transfer Molding:  
Preheat Temperature: 93 to 100°C  
Molding Temperature: 170 to 185°C  
Molding Pressure: 750 to 1000 psi  
Cure Time, 177°C: 1 to 2min  
Post Mold Cure Time, 175°C: 4 to 12 hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

