Evatane® 28-25

Ethylene Vinyl Acetate Copolymer

Arkema

Message:

EVATANE® 28-25 is a random copolymer of Ethylene and Vinyl Acetate made by high-pressure radicalar polymerization process.

The high Vinyl Acetate content of EVATANE® 28-25 brings softness, flexibility and polarity. EVATANE® 28-25 is compatible with most tackifying resins and waxes. Combined with a high fluidity, it is an efficient and easy handling product for hot melt adhesives formulations. EVATANE® 28-25 delivers high cohesive strength with most fillers and may be used to produce masterbatches or HFFR compounds. EVATANE® 28-25 is also suitable for film extrusion.

General Information			
Features	Good Flexibility		
	High Flow		
	Random Copolymer		
	Soft		
Uses	Film		
	Masterbatch		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.950	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16			
kg)	22 to 29	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	27.0 to 29.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	75		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	14.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	800 to 1000	%	ASTM D638, ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	< 40.0	°C	ISO 306/A, ASTM D1525 ¹
Melting Temperature	71.0	°C	ISO 11357-3
Ring and Ball Softening Point ²	120	°C	ASTM E28
NOTE			
1.	Loading 1 (10 N)		
2.	NF EN 1238		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

