# Hostacom X M2 V05 M C12463

### Polypropylene Copolymer

#### LyondellBasell Industries

#### Message:

Hostacom X M2 V05 M C12463 is a 20% talc filled PP copolymer, with good flowability and high stiffness. Product is available as a customized color matched, pellet form. This grade is delivered in C12463 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| General Information                                  |                                   |          |             |
|--|-----------------------------------|----------|-------------|
| Filler / Reinforcement                               | Talc filler, 20% filler by weight |          |             |
| Features   | Rigidity, high                    |          |             |
|  | Copolymer                         |          |             |
|  | Good liquidity                    |          |             |
|  |                                   |          |             |
| Uses   | Application in Automobile Field   |          |             |
|  | Car interior equipment            |          |             |
|  |                                   |          |             |
| Appearance   | Available colors                  |          |             |
| Forms  | Particle                          |          |             |
| Processing Method                                    | Injection molding                 |          |             |
| Physical   | Nominal Value                     | Unit     | Test Method |
| Density (23°C)                                       | 1.05                              | g/cm³    | ISO 1183/A  |
| Melt Mass-Flow Rate (MFR) (230°C/2.16                |                                   |          |             |
| kg)  | 20                                | g/10 min | ISO 1133    |
| Mechanical   | Nominal Value                     | Unit     | Test Method |
| Tensile Stress (Yield, 23°C)                         | 22.0                              | MPa      | ISO 527-2   |
| Impact   | Nominal Value                     | Unit     | Test Method |
| Charpy Notched Impact Strength                       |                                   |          | ISO 179/1eA |
| -40°C  | 1.5                               | kJ/m²    | ISO 179/1eA |
| 23°C   | 5.0                               | kJ/m²    | ISO 179/1eA |
| Notched Izod Impact                                  |                                   |          | ISO 180/1A  |
| -40°C  | 2.0                               | kJ/m²    | ISO 180/1A  |
| 23°C   | 4.5                               | kJ/m²    | ISO 180/1A  |
| Thermal  | Nominal Value                     | Unit     | Test Method |
| Heat Deflection Temperature (0.45 MPa<br>Unannealed) | 110                               | °C       | ISO 75-2/B  |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

