

KOPELEN J-370A

Polypropylene Impact Copolymer

Lotte Chemical Corporation

Message:

J-370A is high impact block copolymer which has high ethylene-propylene rubber content.

This grade is designed to be processed in Injection molding equipments by improvement in mold release and anti-static.

J-370A show high melt flow, low blush and has good balance of strength, impact resistance.

General Information			
UL YellowCard	E85371-251712		
Features	Antistatic		
	Block Copolymer		
	Blush Resistant		
	Good Impact Resistance		
	Good Mold Release		
	Good Strength		
	High Flow		
Uses	Appliances		
	Compounding		
	Containers		
RoHS Compliance	RoHS Compliant		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	26.5	MPa	ASTM D638
Tensile Elongation (Break)	> 50	%	ASTM D638
Flexural Modulus	1470	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-10°C	29	J/m	
23°C	59	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	125	°C	ASTM D648

Flammability	Nominal Value	Test Method
Flame Rating	HB	UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

