

INEOS LDPE 23L430B

Low Density Polyethylene
INEOS Olefins & Polymers Europe

Message:

- Benefits & Features
- 23L430B special polymer structure gives the following properties:
 - Excellent draw down ability with adequate neck-in and stable edges
 - Good process ability also at high line speeds and/or low coating weights
 - Low fumes during extrusion
 - Good adhesion on many substrates
 - Good heat sealing properties
 - Good organoleptical properties
 - Low permeability to moisture and gases
 - Good scratch resistance
 - High purity and very low gel level

Applications

23L430B is a low density polyethylene homopolymer for general coating applications.

23L430B coated substrates such as paper, board and aluminium can be used for packaging food and liquids, powders, medical devices, agricultural materials, chemicals and many other products.

General Information	
Features	Additive Free
	Good Adhesion
	Good Drawdown
	Good Heat Seal
	Good Organoleptic Properties
	Good Processability
	High Purity
	Homopolymer
	Low Density
	Low Gas Permeability
	Low Gel
	Low Moisture Vapor Transmission
	Low to No Fumes
	Scratch Resistant
Uses	Agricultural Applications
	Coating Applications
	Foil Coatings
	Food Packaging
	Medical Packaging
	Packaging
RoHS Compliance	Paper Coatings
	Contact Manufacturer

Forms	Pellets
Processing Method	Extrusion Coating Injection Molding

Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.923	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.5	g/10 min	ISO 1133
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	98.0	°C	ISO 306/A50
Melting Temperature (DSC) ¹	113	°C	Internal Method
Extrusion	Nominal Value	Unit	
Melt Temperature	280 to 325	°C	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

