Vexel B12GF15

Polybutylene Terephthalate Custom Resins Group

Message:

General purpose 15% glass fiber reinforced PBT polyester resin

Has the high chemical and heat resistance of PBT combined with improved strength and stiffness

Suitable for brackets, levers, electrical connectors, housings and other similar uses

| General Information | | | |
|-----------------------------------|----------------------------------|-------|-----------------|
| Filler / Reinforcement | Glass Fiber,15% Filler by Weight | | |
| Features | General Purpose | | |
| | Good Chemical Resistance | | |
| | Good Stiffness | | |
| | Good Strength | | |
| | High Heat Resistance | | |
| Uses | Connectors | | |
| | General Purpose | | |
| | Housings | | |
| Discourse | No order IVolor | 11.9 | To d Marilla al |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.41 | g/cm³ | ASTM D792 |
| Molding Shrinkage - Flow | 0.50 to 0.70 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength | 89.6 | МРа | ASTM D638 |
| Flexural Modulus | 4480 | MPa | ASTM D790 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact (23°C) | 48 | J/m | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 0.45 MPa, Unannealed | 207 | °C | |
| 1.8 MPa, Unannealed | 188 | °C | |
| Peak Melting Temperature | 227 | °C | ASTM D3418 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

