

U-polymer P-1001

Polyarylate

UNITIKA Plastics Division

Message:

P series resins are resins succeeding the characteristics of the neat polymer, U-100, and improved in flowability and optical properties. Among many super engineering plastics, the resins are few transparent polymer alloys that have heat resistance. The heat-stable P-series resins have variations different in heat resistance in the range from 150 to 175°C. There are few transparent heat-resistant resins among super engineering plastics, and thus P series resins are valuable. The resins have favorable weather resistance, and in particular, the P- 1001 resin is approved by SAE Standard (J576 and J578) and FMVSS Standard (108). Making the most of these characteristics, the resins may be used, for example, as the lenses for automobile lamps. High flow-type resins, P-1001A, and P-3001S, are also available for thin molding products.

General Information			
UL YellowCard	E47924-239920		
Additive	Heat Stabilizer		
Features	Amorphous		
	Good Creep Resistance		
	Good Dimensional Stability		
	Good Flow		
	Good Impact Resistance		
	Good Weather Resistance		
	Heat Stabilized		
	High Heat Resistance		
	Opticals		
Uses	Automotive Applications		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.00 mm)	0.80	%	ASTM D955
Water Absorption (24 hr, 3.18 mm)	0.26	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	123		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	69.0	MPa	ASTM D638
Tensile Elongation (Break)	65	%	ASTM D638
Flexural Modulus	2100	MPa	ASTM D790
Flexural Strength	82.0	MPa	ASTM D790
Compressive Strength	81.0	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	260	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648
CLTE - Flow	6.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+16	ohms·cm	ASTM D257
Dielectric Strength	31	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.00		ASTM D150
Dissipation Factor (1 MHz)	0.010		ASTM D150
Arc Resistance	127	sec	ASTM D495
Optical	Nominal Value	Unit	Test Method
Transmittance (3000 μm)	87.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	120 to 140	°C	
Drying Time	6.0 to 8.0	hr	
Rear Temperature	310	°C	
Middle Temperature	340	°C	
Front Temperature	350	°C	
Nozzle Temperature	360	°C	
Mold Temperature	130	°C	
Injection Pressure	137	MPa	
Back Pressure	0.981	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

